


Image<sup>®</sup> Digicolor<sup>®</sup> Silk & Gloss have been specially designed for very high-quality digital printing on dry toner digital presses.



- Tested and recommended by leading dry toner Original Equipment Manufacturers!
- **Key benefits:** faithful colour reproduction, sharp contrasts and extremely vivid colours.
- **Applications:**  
Digital Communication: promotional documents, brochures, newsletters, greeting cards, post cards, business cards, invitations, letterheads, menus, direct marketing...  
Digital Publishing: high-volume laser work like books, manuals, catalogues, etc.
- Image<sup>®</sup> Digicolor<sup>®</sup> is also available with an uncoated finish.



## Image<sup>®</sup> Digicolor<sup>®</sup> Gloss

| Basis weight (g/m <sup>2</sup> ) | ISO 536    | 100  | 115  | 135  | 150  | 170  | 200  | 250  | 300  | 350  | 400  |
|----------------------------------|------------|------|------|------|------|------|------|------|------|------|------|
| CIE Whiteness (%)                | ISO 11475  | 126  | 126  | 126  | 126  | 126  | 126  | 126  | 126  | 126  | 126  |
| Opacity (%)                      | ISO 2471   | 91   | 92.5 | 95   | 96   | 97   | 98   | 99.5 | 100  | 100  | 100  |
| Brightness (%)                   | ISO 2470-2 | 98   | 98   | 98   | 98   | 98   | 98   | 98   | 98   | 98   | 98   |
| Bulk (cm <sup>3</sup> /g)        | ISO 534    | 0.74 | 0.73 | 0.73 | 0.73 | 0.74 | 0.74 | 0.76 | 0.78 | 0.80 | 0.81 |
| Dynamic stiffness MD (mNm)       | ISO 5629   | 0.30 | 0.42 | 0.65 | 0.85 | 1.30 | 2.00 | 4.00 | 7.00 | 11.8 | 19   |
| Dynamic stiffness CD (mNm)       | ISO 5629   | 0.17 | 0.27 | 0.45 | 0.55 | 0.85 | 1.40 | 2.80 | 4.60 | 7.90 | 12.5 |
| Gloss (%)                        | ISO 8254-1 | 73   | 73   | 73   | 73   | 73   | 73   | 73   | 73   | 73   | 73   |

These values are to be considered only as indications and are subject to change according to trade tolerances in the quality specification.  
Issue date: September 2016

